

Divinycell H has been widely used over many years in virtually every application area where sandwich composites are employed including the marine (leisure, military and commercial), land transportation, wind energy, civil engineering/infrastructure and general industrial markets. In its application range Divinycell H has the highest strength to density ratio. It exhibits at both ambient and elevated temperatures impressive compressive strength and shear properties. In addition the ductile qualities of Divinycell H make it ideal for applications subject to fatigue, slamming or impact loads.

Other key features of Divinycell H include consistent high quality, excellent adhesion/peel strength, excellent chemical resistance, low water absorption and good thermal/acoustic insulation. Divinycell H is compatible with virtually all commonly used resin systems (polyester, vinyl ester and epoxy) including those with high styrene contents. Its good temperature performance with high residual strength and good dimensional stability, makes Divinycell H ideal for hand laminating, vacuum bagging, RTM (resin transfer molding) or vacuum infusion.

Technical Data for Divinycell H Grade

Property	Method	Unit	H35	H45	H60	H80	H100	H130	H160	H200	H250
Compressive Strength ³⁾	ASTM D 1621	MPa	0.45	0.6	0.9	1.4	2.0	3.0	3.4	5.4	7.2
		psi	65	87	130	203	290	435	493	783	1,044
Compressive Modulus ³⁾	ASTM D1621	MPa	40	50	70	90	135	170	200	310	400
		psi	5,800	7,250	10,150	13,050	19,575	24,650	29,000	44,965	58,015
Tensile Strength ³⁾	ASTM D 1623	MPa	1.0	1.4	1.8	2.5	3.5	4.8	5.4	7.1	9.2
		psi	145	203	261	363	508	696	783	1,030	1,334
Tensile Modulus ³⁾	ASTM D 1623	MPa	49	55	75	95	130	175	205	250	320
		psi	7,105	7,975	10,875	13,775	18,850	25,375	29,730	36,250	46,400
Shear Strength	ASTM C 273	MPa	0.4	0.56	0.76	1.15	1.6	2.2	2.6	3.5	4.5
		psi	58	81	110	167	232	319	377	508	653
Shear Modulus	ASTM C 273	MPa	12	15	20	27	35	50	73	73	97
		psi	1,740	2,175	2,900	3,915	5,075	7,250	10,590	10,590	14,070
Shear Strain	ASTM C 273	%	9	12	20	30	40	40	40	45	45
Nominal Density ³⁾	ISO 845	kg/m ³	38 ²⁾	48 ¹⁾	60 ¹⁾	80 ¹⁾	100 ¹⁾	130 ¹⁾	160 ¹⁾	200 ¹⁾	250 ¹⁾
		lb/ft ³	2.4 ²⁾	3.0 ¹⁾	3.8 ¹⁾	5.0 ¹⁾	6.3 ¹⁾	8.1 ¹⁾	10.0 ¹⁾	12.5 ¹⁾	15.6 ¹⁾
1) Typical density variation ± 10%.											
2) Typical density variation –10% to + 20%.											
3) Perpendicular to the plane. All values measured at +73.4°F (23°C).											

Continuous operating temperature is –325°F to +160°F (–200°C to +70°C). The foam can be used in sandwich structures, for outdoor exposure, with external skin temperatures up to +185°F (+85°C). For optimal design of applications used in high operating temperatures in combination with continuous load, please contact DIAB Technical Services for detailed design instructions. Normally Divinycell H can be processed at up to +194°F (+90°C) with minor dimensional changes. Maximum processing temperature is dependent on time, pressure and process conditions. Therefore users are advised to contact DIAB Technical Services to confirm that Divinycell H is compatible with their particular processing parameters. Coefficient of linear expansion: approx. $22.2 \times 10^{-6}/^{\circ}\text{F}$ ($40 \times 10^{-6}/^{\circ}\text{C}$)



www.diabgroup.com

This data sheet may be subject to revision and changes due to development and changes of the material. The data is derived from tests and experience. The data is average data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect of the material or its use. The company reserves the right to release new data sheets in replacement.

All content in this publication is protected by International Copyright Laws.
Copyright © DIAB October 2012

H.ds-u/10_2012.rev7